


Vulcan Nexus Cladding



Overview

Vulcan Nexus Cladding is created from thermally modified New Zealand plantation timber and engineered with a patented vertical grain construction for superior weathering characteristics. Finger jointing the timber prior to lamination creates long lengths of timber up to 6 meters long and a unique aesthetic. A fine sawn face allows a depth of grain, and optimal coating performance.

The thermal modification process and vertical grain structure means Vulcan Nexus Cladding has enhanced stability, reduced resin content and is a beautiful homogeneous brown colour.

Available in a range of architectural profiles and can be supplied factory coated in Abodo Protector – Abodo's high performance penetrating exterior oil.

Ensure adequate inspection of samples, existing projects and other references prior to selecting Vulcan Cladding or Vulcan Nexus Cladding.

Wood species: Thermally Modified Radiata Pine (Pinus Radiata).

Standard profiles:



WB10 138x20*
(118mm cover) Vertical/Horizontal



WB12 138x20
(118mm cover) Vertical

*Also available in Vulcan Cladding (see separate Technical Data Sheet).

Lengths: Typical: 3.6m, 5.4m and 6.0m.


Lengths are subject to availability at time of order. Please check with local resellers for pricing, availability, and lead times.

Vulcan Nexus Cladding

Colours: Colours are indicative only and as they would appear on Vulcan timber. Protector – Water Borne is a pigmented penetrating natural oil and is an Abodo proprietary product.

Colour may change/fade as a part of the natural weathering process. See abodo.com.au for Maintenance Guide.

Vulcan Nexus Cladding is usually factory pre-coated with 1 or 2 coats in a colour as selected.



Protector Nero

Protector Ebony

Protector Walnut

Protector Graphite

Protector Teak

Protector Natural

Protector Patina

Protector Straw

Sioo:x*

* Sioo:x is a specialist 3 coat exterior coating system for a long term silver weathered look. Refer Sioox Manual abodo.com.au

Product specifications

Name:	Abodo Vulcan Nexus Cladding.
Quality:	Finger Jointed Select Grade/ Individual laminations finger jointed. Front face and edges virtually free of any defects but with one edge knot and one small face defect allowed per piece in 20% of boards only. Back side with some defects, lamination stepping and skip dress allowed.
Finish:	Fine bandsawn face as standard (some variation in the visual appearance of the bandsawn finish can be expected).
Durability:	Class 1 (EN350-1), Class 2 above ground (AS5604).
Treatment:	Thermally modified – INTENZ Thermowood 230 degrees schedule. TPX 'H2F' treated (AS1604). Available optionally H3 LOSP treated (AS1604).
Insect attack:	TPX suitable for use in areas south of Tropic of Capricorn. H3 LOSP treated suitable for use in all areas.
Intended use:	Intended for above ground use in residential and light commercial buildings.
Serviceable life:	30 years or more when maintained according to manufacturer's recommendations.
Warranty:	15 years against fungal and termite attack (subject to terms and conditions). See separate Warranty Statement
Moisture content:	Approx. 7% MC (+/-2%) at time of dispatch.
Construction:	Fingerjointed and laminated with vertical grain orientation.
Glue:	New generation polyurethane adhesive – VOC, solvent and formaldehyde free. Exterior Type 1 - AS/ NZS4364. Approved for Service Class 3 (exposed exterior applications) (AS1328).
Expected dimensional change in structure:	Width expansion approx 2%, length expansion approx 0.25%, thickness expansion approx 2.5% (from 7%MC to fibre saturation – variation will occur between boards).
Average density:	420kg/m ³ .
Fire:	Group 3, (AS5637), please inquire for solutions to cladding in bush fire zones.
Hardness:	Low (2.5kN Janka).
Weight:	-11 kg/m ² .
Thermal properties:	-0.11W/(mK).
pH (indicative):	3.9.
Curved walls (min radius):	WB10 138x20 – 2.3m.



Vulcan Nexus Cladding

Product specifications

Compatibility:	Vulcan has little or no corrosiveness on most metals and can be placed in contact with most building materials Normal PVA, PU, MUF glues and RF resins can be used. Care should be taken to separate from zinc.
Coating:	Vulcan will take most stains, penetrating oils and paints well, though up-take of coating is generally higher than normal. At least one coat must be applied all sides including back face, and at least two coats to the front face and edges with Abodo Protector or other approved proprietary wood stain. Available factory pre-coated.
Patent:	AU Pat. 2012101047.
Certification:	FSC®-certified mixed, No.: SGS-COC-004944.
Environmental Product Declaration (EPD) registration number:	S-P-01543.

Product handling

- Weatherboards and accessories must be kept clean dry, under cover and out of the weather prior to installation.
- Timber must be stored horizontally on bearers at least 100mm off the ground.
- Extra care must be taken during installation so as not to damage the factory finish of the boards.
- Wear dust mask, eye protection when cutting timber.
- Do not burn treated timber. Dispose of off-cuts in lined land fill or an approved furnace.

Fixing overview

- Timber framing is to be in accordance with AS1684, steel framing in accordance with NCC and manufacturer requirements. Studs at max 600mm centres.
- Fix cladding over a water proof, breathable building wrap (sarking), rigid air barrier or other suitable waterproof substrate in conformance with the NCC.
- Weatherboards may direct fixed or fixed over cavity battens. Cavity method is recommended for optimal weather tightness.
- Horizontal cavity battens must be minimum 70x35mm or 45x45mm H3 treated timber with 10mm plastic or timber spacers every 600mm at each stud fixing point.
Vertical cavity battens must be minimum 35x18mm H3 timber structurally fixed to studs..
- Cavity battens must be H3 treated pine structurally fixed to studs with HDG or stainless steel flat head nails or 10g screws staggered at min 300mm centres (when using a 18mm thick cavity batten) or min 600mm centres (when using a 35 or 45mm thick cavity batten) and with min 45mm fixing penetration into stud.
- Fix boards either vertically or horizontally as appropriate to the profile type specified at maximum 600mm centres.
- High quality hot dipped galvanised fixings (secret fixed profiles only) or stainless steel fixings (face fixed profiles) must be used. Stainless steel fixings must be used in sea spray zones in all cases. Note: Silicone bronze/copper fixings can be subject to oxidation during weathering, resulting in discolouration and weeping around fixing head.
- For WB10 or WB12 secret fix profile, use flat head ring shank nails or self drilling self-countersinking head screws so as to achieve 30mm penetration into stud, or 30mm into the stud and batten combined (when using a structural cavity batten only) and positioned 12mm from the tongue edge. Punching/puttying of fixings is not required. Screw fixing is recommended.
- Fixings at ends of boards must be at least 12mm from edge, and must be pre-drilled before applying fastener. Ensure 2mm expansion gap to back of boards.
- All cut end grains, ripped edges and notches must be sealed with timber insecticide preservative such as Tanalised Enseal Clear or equivalent. All exposed end grains must additionally be sealed using Abodo's Protector End Seal or equivalent wax sealer, or Sioo:x End Grain Sealer in the case of Sioo:x coated boards.

Vulcan Nexus Cladding

Fixing overview

- Joins between board ends must be made over studs/battens only, with joins off-set by minimum 400mm, using a 35degree mitre, and application of sealant at the join eg: Sikaflex 11FC. Excess sealant can be cut and peeled away once cured.
- For cavity systems use perforated cavity base closer flashing at base board to allow drainage, air flow and keep out vermin.
- Cladding must finish 100mm above paved surface or 175mm above un-paved surfaces. Base of cladding must not sit directly into flashings or other cladding materials such as masonry. Minimum 5mm gap must be left to flashings allowing fall to shed water away from the wall cavity.
- Use Abodo finishing mouldings backed by corrosion resistant flashings as required, corners, windows, doors and where cladding meets soffit. Fix mouldings with 40mm stainless flat head ring shank nail (hand driven) at max 450mm centres.
- At least one coat of Protector oil or proprietary specified wood stain must be applied to all sides prior to installation and then a further one or two coats applied to exposed face and edges once boards are fixed in place according to manufacturer’s instructions. For other specialty coatings such as Sioo:x refer to specific literature.

Fixing details:





Fig 1 – WB10 Secret Fix

Note: The adjacent is an overview only. Please refer installation manual for full install details.

Exterior mouldings:



Note: Other profiles are available and should be specified according to the system being used.

Vulcan Nexus Cladding

Maintenance

- Wash down every 12 months with gentle detergent, warm water and soft brush.
- If possible it is recommended to apply a further coat of oil after approx 12 months of weathering.
- Make a maintenance check every two summers. Check all weatherboards, junctions, flashings, mouldings and replace or remediate as required to maintain weather tightness of the cladding system.
- Re-coat every 2-3 years or as required to maintain colour and integrity of coating. Re-coat period may be longer or shorter depending on climatic conditions and/or positioning of cladding to the sun. Preparation with Rejuvenator or other similar oxalic timber cleaner is recommended prior to coating.
- For heavily soiled or mouldy areas use Rejuvenator or similar timber cleaner, apply active mouldicide and recoat with penetrating oil.
- For other specialty finishes such as Sioo:x please refer to specific maintenance literature.

Lightening of the timber:



Vulcan Teak
As delivered



Vulcan Teak
Weathered exterior install



Vulcan Sioo:x
As delivered




Vulcan Sioo:x
Weathered exterior install

We cannot guarantee against wear or color changes to any products which result from weather, sun, wind and/or the natural aging process of the wood.

Surface checking:

- Checking (cracks) may be observed on the face and ends of Vulcan timber. Checks are acceptable to install. Checking may become more apparent as the material weathers naturally in place. Fibre pull at laminated glue lines is also possible. These are not defects and are considered a natural part of this wood product. Maintenance with a coating and thorough sealing of end grains with wax sealer will improve long term weathering characteristics.



Laminated glue
seams

Face check

Vulcan Nexus Cladding

Accessories

Abodo Protector – Water Borne, 4L, 10L:



Abodo Protector – End Seal, 1L:



Abodo Stainless Steel Cladding Screw 4.0mm x 45mm
or 4.5mm x 65mm:

